

CLAIMS

1. A process for producing a polyorganosiloxane-
containing resin, comprising mixing a polyorganosiloxane-
containing resin containing 5% by weight or more of volatile
5 siloxane immediately after coagulation and dehydration with
an organic solvent, and filtering the resultant mixture to
decrease a residue in the resin.

2. The process for producing the polyorganosiloxane-
containing resin according to claim 1, wherein the residue
10 is a volatile siloxane.

3. The process for producing the polyorganosiloxane-
containing resin according to claims 1 and 2, wherein the
organic solvent is an alcohol.

4. The process for producing the polyorganosiloxane-
15 containing resin according to claims 1 to 3, comprising
mixing a polyorganosiloxane-containing resin after
coagulation and dehydration with an organic solvent only
once, and filtering the resultant mixture.

5. The process for producing the polyorganosiloxane-
20 containing resin according to claims 1 to 4, wherein the
Calcium content of the resin is 300 to 1,000 ppm.

6. A polyorganosiloxane-containing resin produced by the
process according to any one of claims 1 to 5.

7. A resin composition comprising a thermoplastic resin
25 and/or a thermosetting resin and the polyorganosiloxane-

containing resin according to claim 6.

5

10

15

20

25